

5

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



2

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : A61K 38/28, 9/51		A1	(11) International Publication Number: WO 96/31231
			(43) International Publication Date: 10 October 1996 (10.10.96)
(21) International Application Number: PCT/IE96/00018		(81) Designated States: AU, CA, JP, NZ, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 2 April 1996 (02.04.96)			
(30) Priority Data: 950237 4 April 1995 (04.04.95) IE		Published With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.	
(71) Applicant: ELAN CORPORATION, PLC [IE/IE]; Monksland Industrial Estate, Athlone, County Westmeath (IE).			
(72) Inventor: RAMTOOLA, Zebunnissa; 163 Charlemont, Griffith Avenue, Dublin 9 (IE).			
(74) Agent: ANNE RYAN & CO.; 60 Northumberland Road, Ballsbridge, Dublin 4 (IE).			
(54) Title: CONTROLLED RELEASE BIODEGRADABLE NANOPARTICLES CONTAINING INSULIN			
(57) Abstract <p>A controlled release pharmaceutical formulation comprises nanoparticles formed of a biodegradable polycyanoacrylate polymer in which insulin is entrapped, the insulin being complexed to the polycyanoacrylate. These particles are capable of releasing bioactive insulin <i>in vivo</i> at a slower release rate than nanoparticles in which the insulin is free. The formulation may comprise a mixture of nanoparticles in which the insulin is free and nanoparticles in which it is complexed, so as to obtain the desired release profile. The nanoparticles have a preferred loading of 15-25 % w/v insulin and a preferred size of 100-400 nm. Administration may be oral or parenteral, and for oral administration, an enteric coating may be provided to target release to the small intestine. Complexing of the insulin is achieved by the polymerisation of cyanoacrylate monomer in the presence of insulin at a low pH, preferably at pH=2.</p>			

BEST AVAILABLE COPY

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LJ	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

## Description

### Controlled Release Biodegradable Nanoparticles Containing Insulin

#### Technical Field

5 This invention relates to controlled release biodegradable nanoparticle formulations and, in particular, biodegradable polyalkylcyanoacrylate nanoparticles containing insulin or insulin analogues.

#### Background Art

10 Polyalkylcyanoacrylate nanoparticles have been studied as potential drug carriers for sustained release formulations, for drug targeting and for improving the bioavailability of peptides and proteins such as insulin, calcitonin and growth hormone releasing factor (Damgé, C. et al., *Diabetes*, 37:246(51) (1988); Lowe, P. et al., *J. Pharma. Pharmacol.*, 46:547-52 (1994); and Gautier, J. et al., *J. Controlled Release*, 20:67-78 (1992)). The short chain cyanoacrylate monomers, such as *n*-butyl, isobutyl and isohexylcyanoacrylate, are typically used because of their short degradation times and low toxicities.

20 Two methods are commonly employed for the preparation of these nanoparticles: the interfacial polymerisation method and the anionic polymerisation method. In the interfacial polymerisation method, the monomer and the drug are dissolved in an organic phase with polymerisation occurring at the organic-aqueous interface upon addition of the organic phase to an aqueous phase (Al Khouri, N. et al., *Int. J. Pharm.*, 28:125-32 (1986)). This method produces nanocapsules. In general, prior art peptide loaded nanoparticles have been produced by this technique (see, e.g., EP-A-0 608 207; EP-A-0 447 318; and FR-A-2,515,960).

Anionic polymerisation occurs in aqueous media at low pH and is catalyzed by hydroxyl ions. In this method, the drug can be incorporated within the nanoparticle, adsorbed onto the nanoparticles or a combination of both depending on the time of addition of the drug to the polymerisation medium (Couvreur, P. et al., *J. Pharma. Pharmacol.*, 31:331-2 (1979)).

Vidarabine-associated polyalkylcyanoacrylate nanoparticles, which result from vidarabine chemically interacting with the cyanoacrylic monomer during the polymerisation process, have been made using the anionic polymerisation method modified by the mandatory inclusion of dioctylsulfosuccinate in the aqueous media. However, formation of the polyalkylcyanoacrylate/vidarabine complex inactivated the biological activity of the vidarabine (Guise, V., et al., *Pharmaceutical Res.*, 7:736-41 (1990)).

Administration of exogenous insulin can ameliorate metabolic abnormalities in type II diabetes by compensating for reduced endogenous insulin secretion, reducing excessive hepatic glucose production and stimulating glucose uptake. Additionally, non-substitutional insulin administration in non-insulin dependent diabetes is indicated where, without it, satisfactory compensation of diabetes is not achieved. Side effects possible from insulin therapy include weight gain, hyperinsulinemia and hypoglycemia.

Although single or multiple daily subcutaneous injections of insulin are the mainstay of insulin delivery techniques, several other methods of insulin delivery are now available or in development, including (a) continuous subcutaneous insulin infusion by a wearable infusion pump; (b) total or segmental transplantation of a pancreas; (c) transplantation of isolated islet cells; (d) implantation of a programmable insulin pump; (e) oral, nasal, rectal and transdermal mechanisms of insulin delivery; (f) administration of insulin analogues; (g) implantation of polymeric capsules which give continuous or time-pulsed release of insulin; and (h) implantation of a biohybrid artificial

pancreas which uses encapsulated islets. Despite these advances, the ideal delivery of insulin to patients has yet to be developed. For instance, subcutaneous and oral methods of insulin delivery do not currently mimic physiological insulin needs and transplantation requires risky immunosuppression.

Thus, there exists a need for improved insulin formulations, particularly controlled release bioactive oral formulations including those targeted to the small intestine and controlled release parenteral formulations to mimic physiological insulin needs.

#### 10 Disclosure of Invention

This invention provides a controlled release pharmaceutical formulation, which comprises insulin entrapped in a biodegradable polyalkylcyanoacrylate polymer to form nanoparticles, wherein the insulin is complexed to the polyalkylcyanoacrylate.

15 As used herein, the term "insulin" refers to insulin and analogues of insulin having similar physical properties.

As used herein, the term "polyalkylcyanoacrylate" refers to poly(2-12 C (straight or branched chain) alkyl 2-cyanoacrylates. Preferred polyalkylcyanoacrylates include polymers formed from 4-6 C alkylcyanoacrylate monomers such as *n*-butylcyanoacrylate, isobutylcyanoacrylate and isohexylcyanoacrylate or mixtures thereof.

25 As used herein, the term "biodegradable" as applied to polyalkylcyanoacrylate polymers means polymers which are degradable *in vivo* either enzymatically or non-enzymatically to produce biocompatible or non-toxic by-products which can be further metabolized or excreted *via* normal physiological pathways.

The biodegradable polyalkylcyanoacrylate polymer is suitably *n*-butylcyanoacrylate, isobutylcyanoacrylate or isohexylcyanoacrylate monomers or mixtures thereof.

Surprisingly, this invention discloses that at low pH and otherwise  
5 typical anionic polymerisation conditions, insulin complexes with  
polycyanoacrylate during the polymerisation step, forming  
polyalkylcyanoacrylate-complexed insulin-loaded nanoparticles. At  
higher pH, the insulin does not complex with the polymer but, rather, is  
incorporated into nanoparticles as free insulin. Further surprisingly,  
10 the polyalkylcyanoacrylate-complexed insulin-loaded nanoparticles are  
capable of releasing bioactive insulin *in vivo*. The rate of insulin  
release from these polyalkylcyanoacrylate-complexed insulin-loaded  
nanoparticles is slower than that from corresponding free insulin-  
loaded polyalkylcyanoacrylate nanoparticles. At an intermediate pH,  
15 the nanoparticles can be a natural mixture of free and complexed  
insulin.

Thus, this invention provides oral and parenteral formulations  
containing polyalkylcyanoacrylate-complexed insulin-loaded  
nanoparticles that are capable of releasing pharmaceutically effective  
20 amounts of bioactive insulin in a controlled fashion to satisfy  
physiological insulin needs when orally or parenterally administered to  
a subject, particularly a human. Further, the controlled release nature  
of these formulations makes possible the targeting of insulin to the  
small intestine when administered orally, which enhances the  
25 bioavailability of the insulin. Optionally, these oral and parenteral  
formulations may comprise a mixture of polyalkylcyanoacrylate-  
complexed insulin-loaded nanoparticles and free insulin-loaded  
polyalkylcyanoacrylate nanoparticles.

The biodegradable nanoparticles preferably contain 5% to 30%  
30 w/v of insulin to monomer content, more especially 15-25% w/v  
insulin.

The size of the biodegradable nanoparticles suitably is 50-900 nm, preferably 100-400 nm.

5 The polyalkylcyanoacrylate-complexed insulin-loaded nanoparticles in accordance with the invention and, optionally, free insulin-loaded polyalkylcyanoacrylate nanoparticles, if present, are suitably incorporated into oral dosage forms, such as capsules, tablets, powders including powders capable of effervescing upon addition of water, or suspensions. Additionally, an enteric coating can be applied to the polyalkylcyanoacrylate-complexed insulin-loaded nanoparticles and, optionally, free insulin-loaded polyalkylcyanoacrylate  
10 nanoparticles, if present, to protect the formulation while it passes through the stomach to further target release of insulin to the small intestine. Alternatively, the nanoparticles can be administered parenterally to release insulin to mimic physiological insulin needs.

15 Thus, for convenient and effective oral administration, pharmaceutically effective amounts of the nanoparticles of this invention can be tableted with one or more excipient(s), encased in capsules such as gel capsules, formulated with ingredients which upon addition of water, provide an effervescent solution, and suspended in a liquid solution and the like. The nanoparticles can be suspended in a  
20 saline solution or the like for parenteral administration.

When the nanoparticles are tableted, the tablets optionally comprise an enteric coating on the tablet to target release of insulin to the small intestine when administered orally.

25 It will be appreciated that the pharmaceutical formulations in accordance with the invention can be used *inter alia* to provide exogenous insulin to patients with type II diabetes or to treat non-insulin dependent diabetes. Suitably, the formulations of this invention are administered to humans at an insulin dose, which varies from  
30 individual to individual, such that the blood glucose levels are adjusted to stay within normal ranges. The oral formulations preferably are

designed as 4-times daily products while the parenteral formulations, which typically have  $\geq 100$  IU of bioavailable insulin per ml, can be administered once or twice daily up to once weekly.

#### Brief Description of Drawings

5           Figure 1 shows the mechanistic pathway for the anionic polymerisation method of forming polyalkylcyanoacrylate nanoparticles;

10           Figure 2 shows blood glucose levels over six hours expressed as a percentage of baseline values for four groups of male Wistar rats: Control (n=4; untreated rats); insulin solution (n=4; solution containing 2.5 IU insulin administered by IM injection to each rat at time 0); pH = 2 (n=4; aqueous suspension of insulin-loaded polyalkylcyanoacrylate nanoparticles (16 IU) produced at pH = 2 administered by IM injection to each rat at time 0); and pH = 4.8 (n=3; aqueous suspension of insulin-loaded polyalkylcyanoacrylate nanoparticles (16 IU) produced at pH 4.8 administered by IM injection to each rat at time 0); and

15           Figure 3 shows blood glucose levels over 4 hours expressed as a percentage of baseline values for two groups of male Wistar rats: Control (n=8; untreated rats) and Study (n=5; aqueous suspension of insulin-loaded polyalkylcyanoacrylate nanoparticles (204 IU) produced at pH = 2 administered orally to each rat at time 0).

#### Modes for Carrying Out the Invention

25           In the following Examples, *n*-butylcyanoacrylate was donated by Loctite Ltd. (Ireland). Isobutylcyanoacrylate, Dextran 10, 40 and 70 and insulin (bovine) were obtained from Sigma. Surface morphology of the nanoparticles produced was studied by scanning electron microscopy (SEM) (Leica Cambridge S360). Drug loading was monitored by the method of residuals using UV spectroscopy and by

gradient HPLC analysis according to USP XXII. Male Wistar rats were used in the *in vivo* studies and blood glucose levels were monitored by an Ames<sup>TM</sup> Glucostix system.

### Example 1

#### 5      Effect of Choice of Monomer upon Nanoparticle Characteristics

Biodegradable polyalkylcyanoacrylate nanoparticles were produced from *n*- and isobutylcyanoacrylate using the anionic polymerisation method under standard conditions. For instance, for 20% starting drug loading, 100 mg of insulin was dissolved in 49.5 ml of a 0.01M HCl solution containing 0.5% Dextran 70 (as a stabiliser) prior to addition of the monomer. After adding the monomer, e.g., 0.5 ml isobutylcyanoacrylate, the solution was stirred for 4 hours, filtered or centrifuged and dried overnight. No difference in particle morphology between particles formed from *n*- or isobutylcyanoacrylate was observed under these conditions. The surface of particles produced was smooth and free of drug crystals and the particles were 100 nm - 400 nm in diameter. For a starting loading of 20% w/w, insulin loading values of 17.82% for *n*-butylcyanoacrylate and 17.97% for isobutylcyanoacrylate were obtained. Thus, the formation of insulin-loaded nanoparticles was not influenced by the choice of these monomers.

### Example 2

#### Effect of Stabiliser Molecular Weight and Concentration upon Nanoparticle Characteristics

25      Nanoparticles were produced using the method outlined in Example 1 to study the effect of varying the molecular weight of the stabiliser Dextran (using Dextran 10, Dextran 40 and Dextran 70;  $M_w$  = 10,000, 40,000 and 70,000, respectively) at a concentration of 0.5%

5 w/v on nanoparticle formation. Additionally, using Dextran 70, the concentration of the Dextran was also varied from 0.05 to 1% w/v. As shown in Table 1, no difference in nanoparticle size and morphology or in insulin entrapment efficiency was observed when either the molecular weight or concentration of the Dextran used was varied. This result for insulin-loaded polyalkylcyanoacrylate nanoparticles is contrary to that reported for empty polyalkylcyanoacrylate nanoparticles (Douglas, S. et al., *J. Colloid Interface Science*, **103**:154-63 (1985).

**TABLE 1: Influence of Molecular Weight and Concentration of Dextran on Insulin Loading of Nanoparticles**

Dextran Type	Dextran Concentration (% w/v)	Insulin Loading (% w/w)
Dextran 10	0.50	18.00
Dextran 40	0.50	16.90
Dextran 70	0.05	18.04
Dextran 70	0.10	18.53
Dextran 70	0.25	18.25
Dextran 70	0.50	19.07
Dextran 70	1.00	18.18

### Example 3

#### The Effect of Polymerisation Medium pH upon Nanoparticle Characteristics

5

10

Insulin-loaded *n*-butylcyanoacrylate nanoparticles were produced using the method outlined in Example 1 to study the effect of varying the pH of the polymerisation medium from 1 to 4.8 on nanoparticle formation. As the pH of the polymerisation medium was increased above 3, defined, distinct particles were produced having smooth, drug-crystal free surfaces. However, below a pH of 3, formation of distinct nanoparticles appeared to be limited, showing only small quantities of well-formed nanoparticles. At this low pH, the formation of particles

occurs quickly, resulting in the majority of nanoparticles not being well formed.

Additional experimentation shows that a white frothy precipitate results when insulin, at 10% and 20% w/v of monomer content, is first dissolved in a 0.1M HCl solution containing 0.5% w/v Dextran 70 to which 0.25 ml isobutylcyanoacrylate monomer is added. The precipitate can be collected by filtration and dried to give a fine white powder (100-400 nm). This reaction does not occur in the absence of insulin in the HCl solution or if the insulin is added after the cyanoacrylate monomer.

Without being bound by any theoretical explanation, it is suggested that these observations may be explained, with hindsight, by reference to the mechanism by which anionic polymerisation occurs and the physicochemical properties of insulin. As shown in Figure 1, the hydroxyl ions present in the aqueous polymerisation medium initiate polymerisation. Because insulin is a peptide with an isoelectric point of 5.3, at a pH below 5.3 it is positively charged, while at a pH greater than 5.3 insulin is capable of being negatively charged. At low pH (pH  $\leq 2$ ), the insulin molecule has a net charge of +6 and can complex with the negatively charged cyanoacrylate short chains resulting in a termination of the polymerisation process. As the pH of the polymerisation medium is increased to 5, the net charge on insulin approximates zero and, therefore, complexation with the cyanoacrylate short chains is unlikely. At that pH, well formed insulin-loaded nanoparticles are produced.

HPLC analysis of insulin content of the nanoparticles produced at pH 2 yielded no insulin peaks at the expected insulin retention time. However, UV analysis (by the method of residuals) indicated  $\geq 80\%$  drug entrapment. HPLC analysis of nanoparticles produced at pH 4.8 showed the presence of insulin at the expected retention time of 19 minutes. These observations support the conclusion that, at low pH, insulin is complexed with the polymer and is not being eluted at the

expected retention time for free insulin whereas at pH 4.8, free insulin is incorporated in the nanoparticles and is eluted at the expected retention time.

5 To support this conclusion, the formation of empty nanoparticles within the same pH range was investigated in order to establish if the presence of insulin inhibits nanoparticle formation at low pH. Nanoparticles were produced at pH 2, 3 and 4 under the same conditions as those employed for the insulin-loaded nanoparticles. In  
10 all cases, the nanoparticles produced were smooth, spherical and uniform in size. Thus, at low pH, the presence of insulin in the polymerisation medium interferes with nanoparticle formation.

#### Example 4

##### Intramuscular Administration of Insulin-loaded Nanoparticles to Rats

15 The bioactivity and release properties of the insulin-loaded *n*-butylcyanoacrylate nanoparticles produced according to Example 3 were examined by intramuscular (IM) administration to male Wistar rats. Insulin-loaded nanoparticles produced at pH 2 (16 IU) and pH 4.8 (16 IU) were administered in aqueous suspension by IM injection to two groups of rats and blood glucose levels were monitored over a six hour  
20 period. Pure insulin solution (2.5 IU) was administered by IM injection to a third group of rats to provide a comparison between delivery *via* the nanoparticulate formulations and unencapsulated insulin. The blood glucose levels of untreated rats (controls) were also monitored over the same time period.

25 Figure 2 shows the blood glucose levels for the pH 2, pH 4.8, control and untreated groups expressed as a percentage of baseline values. Blood glucose levels in the untreated group were within 87.6 to 108.9% of the baseline value in the study period. Administration of the nanoparticles resulted in a steady reduction in blood glucose levels to  
30 20% of the baseline value, indicating that the insulin from both types of

nanoparticles (complexed at pH 2; free insulin at pH 4.8) is bioactive and is released in a controlled, sustained fashion. The blood glucose reduction was faster for nanoparticles produced at pH 4.8 than for those produced at pH 2, presumably due to the faster release of free insulin from the pH 4.8 formulation as opposed to the slower release of insulin complexed with polyalkylcyanoacrylate in the pH 2 formulation.

### Example 5

#### Oral Administration of Insulin-loaded Nanoparticles to Rats

The bioactivity and release properties of the insulin-loaded *n*-butylcyanoacrylate nanoparticles produced according to Example 3 were examined by oral administration to male Wistar rats. Insulin-loaded nanoparticles produced at pH 2 were administered orally in an aqueous suspension to a group of rats and blood glucose levels were monitored over a four hour period. The dose administered *per* rat was 204 IU of insulin. The blood glucose levels of untreated rats were also monitored over the same time period.

Figure 3 shows the blood glucose levels for these two groups expressed as a percentage of baseline values. Blood glucose levels in untreated rats were between 85 and 100% of the baseline value during the study period. In the treated rats, a reduction in blood glucose levels to 35% of the baseline value was observed over a four hour period giving an oral bioavailability of  $\geq 7\%$  for these insulin-loaded nanoparticles. These results indicate that the insulin from nanoparticles produced at pH 2 (complexed to the polyalkylcyanoacrylate) is bioactive and is released in a controlled, sustained fashion.

Claims:-

1. A controlled release pharmaceutical formulation, which comprises insulin entrapped in a biodegradable polyalkylcyanoacrylate polymer to form nanoparticles, wherein the insulin is complexed to the polyalkylcyanoacrylate.  
5
2. A controlled release pharmaceutical formulation according to Claim 1, wherein the polyalkylcyanoacrylate is formed from *n*-butylcyanoacrylate, isobutylcyanoacrylate or isohexylcyanoacrylate monomers or mixtures thereof.
- 10 3. A controlled release pharmaceutical formulation according to any preceding claim, wherein the insulin loading ranges from about 5% to 30% w/v of monomer content.
4. A controlled release pharmaceutical formulation according to any preceding claim, further comprising free insulin-loaded polyalkylcyanoacrylate nanoparticles to form a mixture of  
15 polyalkylcyanoacrylate-complexed insulin-loaded nanoparticles and free insulin-loaded polyalkylcyanoacrylate nanoparticles.
5. A controlled release pharmaceutical formulation according to any preceding claim, further comprising an enteric coating on the  
20 polyalkylcyanoacrylate-complexed insulin-loaded nanoparticles to target release of insulin to the small intestine when administered orally.
6. A controlled release pharmaceutical formulation according to Claim 4 or 5, further comprising an enteric coating on the free insulin-loaded polyalkylcyanoacrylate nanoparticles to target release of  
25 insulin to the small intestine when administered orally.
7. A controlled release pharmaceutical formulation according to any preceding claim, where the formulation is formulated as

capsules, tables, powders, powders capable of effervescing upon addition of water, or suspensions.


5           8.    A controlled release pharmaceutical formulation according to Claim 7, where the formulation is formulated as tablets and further comprising an enteric coating on the tablet to target release of insulin to the small intestine when administered orally.

          9.    A controlled release pharmaceutical formulation according to any preceding claim and adapted for oral administration.

10          10.   A controlled release pharmaceutical formulation according to any of Claims 1 through 8 and adapted for parenteral administration.


          11.   A controlled release pharmaceutical formulation according to Claim 1, substantially as hereinbefore described and exemplified.

## Figure 1




**R = 2-12C alkyl such as butyl, isobutyl, isohexyl.**

Figure 2



3/3

Figure 3.



**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**